

Product Information Sheet



EPDM Membrane (Firestone)

PIN # 1117

Item Description

45mil & 60mil EPDM Black

9', 11', 13', 15, 16'.7" wide X custom length (45mil)

13' or 15' wide x custom length (60mil)

product Number

PE-450009,PE-451010,

PE-451304,PE-451510

PE-451600,PE-600103

PE-600105

Product Information

Firestone FR RubberGard EPDM is a non-reinforced, cured, single-ply roofing membrane that can be used in ballasted, fully adhered and mechanically attached systems.

Method of Application:

Can be used as an elastomeric single-ply roofing membrane for new construction and re-roofing and modular applications. May be installed in Ballasted and Fully Adhered roofing systems.

Typical Properties:

Typical Properties

Property	ASTM Standard	Units	Performance	Typical	Typical
Thickness, min Sheet-overall	D4 12	in. (mm)	45 mil: .0405(1.028)	.0405 (1.028)	.059 (1.499)
Tensile Strength, min	D412 (Die C)	psi(MPa)	1305 (9.0)	1465 (10.1)	1454 (10.0)
Elongation, Ultimate, min	D412 (Die C)	%	30	35	62
Tensile set, max	D412 Method A (Die	%	1	5	2.1
Tear Resistance, min	D624 (Die C)	lbf/in(kN/m)	159 (26.3)	190 (33.2)	219 (38.4)
Brittleness Point, max	D21	°F (°C)	10 (45)	-62 (-52)	-49 (-45)
Ozone Resistance, no	D11	-	-49 (-45)	-65 (-54)	Pas
Heat Aging: Tensile Strength, min	D5 73 D412 (Die C) D412	- psi(MPa) a) %	1205 (8.3)	1450 (10.0)	1490(10. 3) 32
Elongation, ultimate, min	D6	% lbf/in(kN/m)	20 0	22 5	2 17
Water Absorption, max,	D4	%	+8,-	+1.	+1.5
Factory Seam Strength, min	D816 Method B	lbf/in(kN/m)	50(8.8) or Sheet	Sheet Failure	Sheet Failure
Weather Resist ance: Visual	D5 18 D5	- % %	Pa ss 3	Pas s 6	Pas s 5
Air Permeance (Material):	E217	ft ³ /ft ²	<0.004 (0.02))	Pas	Pas

For further information contact
RPW Associates, Inc
905-875-1108 / 866-202-6900

Product Information Sheet



**The ASTM 2178 values listed are for the air permeance of the FR RubberGard EPDM Membrane component only. For use of the product as a component in an air barrier assembly, please consult your Firestone Technical Advisor. Code Agency or Authority having*

Storage:

- Store away from sources of punctures and physical damage.
- Assure that structural decking will support the loads incurred by material when stored on rooftop. The deck load limitations should be specified by the project designer.
- Store away from ignition sources as membrane will burn when exposed to open flame.

Precautions:

Review Safety Data Sheets (SDS) prior to use.

- Take care when moving, transporting, handling, etc. to avoid sources of punctures and physical damage.
- Isolate waste products, such as petroleum products, greases, oils (mineral and vegetable) and animal fats from the RubberGard membrane.
- It is important that the side of the sheet imprinted with the direction "This Side Down" be installed in direct contact with the substrate to achieve respective test agency compliance.

For further information contact
RPW Associates, Inc
905-875-1108 / 866-202-6900